

PRODUCT DATA

Date: March 2011

Information Sheet No.: 03288/24

TENSOL 70

EVO-PLAS RANGE - TWO COMPONENT CEMENT

EVO-PLAS TENSOL 70 is a two component acrylic cement that hardens at room temperature by polymerisation. It produces high strength bonds to acrylic sheet and offers excellent weathering resistance.

RECOMMENDED USE

EVO-PLAS TENSOL 70 is intended for cementing acrylic sheet to itself, but it will bond acrylic sheet to other materials such as wood. Applications include sign making, model making, structural engineering and acrylic sheet repair. Unsupported gaps of up to 1mm can be produced.

EVO-PLAS TENSOL 70 is not recommended for structural applications on aircraft.

BONDING INSTRUCTIONS

SURFACE PREPARATION

- Substrates to be bonded should be perfectly clean, dry and free from dust and grease.

APPLICATION / BONDING

- EVO-PLAS TENSOL 70 Component A** must be at room temperature i.e. 16 - 20°C. If it has been stored below 15°C it must be allowed to come to room temperature before use. This could take several hours.
- MIXING RATIO By Weight**

EVO-PLAS TENSOL 70 Component A	20 parts
EVO-PLAS TENSOL 70 Component B	1 part

The cement will not harden properly if different proportions are used.

- Add **Component B** to **Component A** and mix thoroughly, after mixing cover the vessel and leave until the larger bubbles have risen to the surface.
- The bubbles should be allowed to rise and the job completed within 20 minutes of adding **Component B**, hardening begins as soon as **Component B** is added, if not used within 20 minutes the bond will be weakened.
- Cementing operations should not be undertaken at temperatures below 15°C otherwise the setting time may be affected. Ideally the room temperature should be 15 - 25 °C.
- Setting begins as soon as **Component B** is added, the cement should harden within 1.5 - 2 hours at 20+/- 5°C, after this time the joint can be handled carefully. Light machining is possible after approx. 4 hours, but a better finish and stronger joint will be obtained if left for 24 hours.
- Once set the cement continues to harden for some time - after several days the bond strength should be adequate for most applications. However the strength of joints can be increased further by heat treatment
 - Non thermoformed components - heat for 3 - 4 hours at 80°C.
 - Thermoformed, highly stretched components - heat for 4 - 5 hours at 70°C.
 - Do not heat components until at least 1 hour after cement has set.
- Gap filling - Because of its low viscosity the gap filling properties of **TENSOL 70** are limited. Special masking techniques will be needed to keep the cement in place if large gaps are to be

filled. In addition the cement shrinks in volume by Approx. 20% as it hardens so cavities must be over filled to allow for this

- Colour - After prolonged outdoor exposure (years) in warm climates a slight yellowing of the bond line may appear. This will not effect the mechanical properties of the cement.
 - If **Component B** becomes deeply coloured (yellow/orange) the hardening time should be tested by mixing a small amount of the two components. Obtain a new bottle of **Component B** if the cement is slow to set.

TYPICAL CHARACTERISTICS

	Component A	Component B
Physical Form:	Mobile syrup	Liquid
Colour	Slight blue tinge	Pale straw
Chemical Type:	Acrylic	Peroxide
Solvent	Methyl Methacrylate	Plasticiser
Viscosity (Brookfield RVT, 10rpm at 25°C)	Approx. 1500 mPas	
Solids Content:	100%	Approx. 5%
Specific Gravity:	Approx. 1.03	Approx. 1.2
Flammability:	Highly Flammable	Oxidising agent
Cleaner / Thinner	EVO-STIK CLEANER 5	

PACKAGING

Please refer to the Customer Service Department for current pack sizes.

STORAGE

Component A - store in the dark in a dry flameproof area below 20°C.

Component B - store in the dark at 0 - 5°C. At lower temperatures component B may crystallise out of solution. It is important that all solid deposits are re-dissolved before use. This should be done by **carefully** by warming to Approx. 20°C and shaking.

SHELF LIFE

12 months from date of manufacture stored under the above conditions.

MATERIAL SAFETY DATA

For further information refer to the relevant Health and Safety Data Sheet.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Bostik Limited, Ulverscroft Road, Leicester, LE4 6BW England. Tel: +44 (0)1785 272625 Fax: +44 (0)116 253 1943

www.Bostik.co.uk